



Army Corrosion Summit 2010, Huntsville
I. Carl Handsy, Dan Nymberg



TECHNOLOGY DRIVEN. WARFIGHTER FOCUSED.

Replacement for Cadmium Plating and Hexavalent Chromium on Fasteners and Electrical Connectors

February 10, 2010

I. Carl Handsy, Dan Nymberg, Scott Porter

Report Documentation Page				Form Approved OMB No. 0704-0188	
Public reporting burden for the collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to a penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
1. REPORT DATE 10 FEB 2010		2. REPORT TYPE		3. DATES COVERED 00-00-2010 to 00-00-2010	
4. TITLE AND SUBTITLE Replacement for Cadmium Plating and Hexavalent Chromium on Fasteners and Electrical Connectors				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S)				5d. PROJECT NUMBER	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Tank-Automotive Comd -TARDEC-RDECOM,AMSTA-TR-E1 MEPS1267,6501 E Mile Rd,Warren,MI,48397-5000				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited					
13. SUPPLEMENTARY NOTES 2010 U.S. Army Corrosion Summit, Huntsville, AL, 9-11 Feb					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT Same as Report (SAR)	18. NUMBER OF PAGES 21	19a. NAME OF RESPONSIBLE PERSON
a. REPORT unclassified	b. ABSTRACT unclassified	c. THIS PAGE unclassified			

- Objective
- Guidance
- Background
- Technical
- Coordination
- Feedback
- Test Update/Future Testing
- Path Forward
- Q&A

- Replace cadmium plating and hexavalent chromium post treatment with high purity aluminum and tri-valent chromium conversion coating
- The intention is to make high purity aluminum the default replacement for fasteners and electrical shell connectors currently plated with cadmium, where technically permissible.

- Office of the Secretary of Defense Directive
 - “Approve the use of alternatives [to **hexavalent chromium**] where they can perform adequately for the intended application and operating environment.”
- 29 CFR 1910.1200
 - Asbestos, beryllium, radioactive materials, **hexavalent chromium**, (electroplating and coatings), **cadmium** (electroplating), mercury, or other highly toxic or carcinogenic materials
- European Union (EU) RoHS and REACH legislation restricts or bans many hazardous materials including hexavalent chromium, cadmium, and lead. Currently, the legislation does apply to the Military.

- Advantages of Cadmium
 - It works
 - Applies to majority of materials and uses
 - Cheap and available
- Disadvantages
 - Chromium and cadmium are carcinogens
 - DoD directives to eliminate both

- Numerous alternatives
 - Zinc nickel (Zn/Ni)
 - Tin zinc (Sn/Zn)
 - Zinc (Zn)
 - Aluminum (Al)
- Commercially Organic Coatings (e.g.)
 - Magni
 - Elisha
 - Geomet
 - Xylon

Numerous coating choices may seem **attractive; however...**

- Creates complexity for design, maintenance, & supply
- No configuration control
- No comprehensive knowledge of new galvanic couples introduced in joint designs
- Potential torque conflicts
- Hardness of mating surfaces
- Example: A joint released with a Zn-rich inorganic coated (Geomet) bolt, a Zn-Ni washer, and a Ni coated nut, mated to an aluminum substrate, would result in a galvanic corrosion issue.

- The *good news* is that we have many choices
 - Competition
 - Availability

- The *bad news* is that we have many choices
 - Material compatibility
 - Logistics tail
 - Compatibility with legacy systems such as existing halves of cadmium plated connectors



Technical Aluminum vs. Cadmium Plating



- Aluminum Corrosion Performance –equivalent at same thickness
- Heat Resistance – Trivalent Chrome protects up to about 400 °F; Hexavalent Chrome fails at about 140 °F.
- Lubricity and Clamping is equivalent with friction modifier
- Galling – low risk with friction modifiers
- Volume of aluminum corrosion product increases, but not significantly vs cadmium



Technical - Why aluminum?

Galvanic series



Noble / Cathodic

- Platinum
- Gold
- Graphite
- Titanium
- Silver
- 18-8Mo stainless steel (passive)
- 18-8 stainless steel (passive)
- Chromium stainless steel 11–30% Cr (passive)
- Inconel (passive) (80Ni-13Cr-7Fe)
- Nickel (passive)
- Silver solder
- Monel (70Ni-30Cu)
- Cupronickels (60–90Cu, 40-10Ni)
- Bronzes (Cu-Sn)
- Copper
- Brasses (Cu-Zn)
- Inconel (active)
- Nickel (active)
- Tin
- Lead
- Lead-tin solders
- 18-8Mo stainless steel (active)
- 18-8 stainless steel (active)
- Ni-Resist (high-nickel cast iron)
- Chromium stainless steel, 13% Cr (active)
- Cast iron
- Steel or iron
- Aluminum alloy 2024
- **Cadmium**
- Aluminum alloy 1100
- **Aluminum (high purity)**
- Zinc
- Magnesium and magnesium alloys

Active / Anodic



Technical - Plating Equipment / Process Comparison



	Cadmium	Aluminum
Plating Tanks	Standard	Standard
Anode	Standard	Standard
Tooling	Standard	Standard
Rectifier	Standard	Standard
Gantry	Standard	Standard
Plating Method	Rack or Barrel	Rack or Barrel
Bath Chemistry	HAZMAT Restricted	HAZMAT Restricted
Bath Chemistry	Aqueous Based	Non-aqueous
Hydrogen Embrittlement	Yes - Coated parts require 23+ hr bake at about 400 °F	No - No post-bake needed
Waste Stream Disposal	HAZMAT Landfill	Non-HAZMAT Blended Fuels
Plating Line Enclosure	No	Yes - plus nitrogen blanket to keep air & moisture out

- Automotive
 - Cladding of structural aluminum and steel parts
 - Aluminized mufflers
- Aircraft
 - Skin cladding
 - High strength landing gear (No hydrogen embrittlement)
- Application methods
 - Plating (toluene and ionic salt), flame spray, hot dip, rolling, ion vapor deposition, etc.



- TARDEC has received comments and questions from
 - Government
 - DLA
 - DSCC has not concurred with this initiative
 - US Navy
 - US Air Force
 - ASETS Defense 09
 - Industry
 - Aviation industry
 - Boeing, Pratt & Whitney, Lockheed
 - Fastener manufacturers
 - Ground Equipment OEMs
 - Electrical connector OEM
 - SAE

- Contract let with US2 Inc. for Business case/future costs and availability analysis
- Received list of 10 interested suppliers from survey performed by Automation Alley in Michigan who are interested in application of high purity aluminum coatings.

- Why all DoD
- Aircraft community comments/perspective on introduction of different products/coating
- Business questions
- Technical questions

Cost

- *Implementation*
 - *Life Cycle cost*
 - *Procurement, Maintenance, Tracking of HAZMAT, Disposal/DEMIL*
- Availability
- Producibility
- Industrial supply base
- Capacity
 - Present, Future, Ramp up time
- Demand creation
- Competition

- Corrosion/persistency of coating
- Galling
- Adequacy of testing
- Lubricant compatibility
- Processing
- Conductivity
- Aerospace requirements
- Rework and availability of alternatives
- Exposure to toluene in plating process

- CTC Fastener study
 - Corrosion, lubricity, mechanical coupling and decoupling
- RESET program
 - Installed aluminum wheel studs on Stryker vehicles, inspected after 7 months in Hawaii



- Quantify effects of Tri Chrome thickness on lubricity, wear resistance and corrosion
- Future development
 - Engineer combined durable and lubricious coating for large shell connector coupling and decoupling similar to current cadmium performance

- TARDEC continues to staff a DoD policy to the Office of the Secretary of Defense through the Army Corrosion Executive for the replacement of cadmium plated fasteners and electrical connectors with high-purity aluminum
- Need to evaluate present test methods with regard to material qualification
- Based on above study, need to re-evaluate test method in current MIL-Stds.
 - E.g., salt spray vs. cyclic corrosion testing, and outdoor exposure to correlate to field conditions and use



Cadmium/Hex-Chrome Replacement



Questions and Discussion